



Desoprime™ HS CA7233 Military Epoxy Primer

TECHNICAL DATA SHEET

Product Description

Desoprime™ HS CA7233 is a high solids corrosion, chemical, and solvent resistant, military epoxy primer used on the exterior of aircraft. CA7233 has excellent adhesion to a variety of substrates and exhibits a high degree of Skydrol® resistance.

- Compatible with Desothane® HS topcoats
- Passes the rain erosion test
- Service temperature -54°C to 177°C (-65°F to 350°F)

Components



Mix ratio (by volume):

- | | |
|---------------------------------|--------|
| • CA7233A (base component) | 1 part |
| • CA7233B (activator component) | 1 part |

Specifications



CA7233 epoxy primer is qualified to:

- | | |
|--|---------------------------------|
| • MCS 9053 Type I Class 1
Grade 1 & 2 | • MIL-PRF-23377 Type I Class C2 |
| • MIL-PRF-53039 | • MIL-PRF-64159 |

Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.

Product Compatibility:

CA7233 primer is compatible with the following topcoat specifications:

- | | |
|------------------------------|-----------------|
| • AIMS 04-04-013 | • DPM 6456 |
| • BAMS 565-009 | • DPM 6546 |
| • BMS 10-60 Type I & Type II | • MIL-PRF-85285 |
| • BMS 10-72 Type VIII | • MMS 420 |
| • DMS 2115 | |

Surface Preparation and Pretreatments



Desoprime™ CA7233 primer can be applied over clean, dry, intact aluminum and composite surfaces. Aluminum surfaces shall be treated with materials conforming to MIL-C-5541 or equivalent.



PPG Aerospace
Coatings





Desoprime™ HS CA7233 Military Epoxy Primer

Application Guidelines

Recommended Application Conditions:

Temperature	15 - 30°C (59 - 86°F)
Relative Humidity	20 - 90%

Application:


Ground the aircraft and the application equipment before priming. Stir the primer slowly during the application. The suggested film thickness is 15 to 30 microns (0.6 to 1.2 mils). This can be accomplished by one medium coat with a 50% overlap

These application guidelines represent PPG's best advice in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.



Theoretical Coverage:

18 square meters/liter at 25 microns dry film (722 square feet/gallon at 1 mil dry film)
Recommended dry film thickness; 15 to 30 microns (0.6 to 1.2 mils)



Dry Film Density:

1.76 grams/cubic centimeter (14.66 pounds/gallon)

Dry Film Weight:

44 grams/square meter at 25 microns dry film (0.009 pounds/square feet at 1 mil dry film)

Desoprime™ HS CA7233 Military Epoxy Primer



Equipment:

CA7233 primer is compatible with all current forms of spray equipment.

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
Electrostatic Air Spray Gun	1.2 mm or 1.5 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)
Electrostatic Air Assisted Airless Spray Gun	#611 or #613 (Graco Nomenclature)	700 to 1200 psi (48 to 82 bar)	40 to 60 psi (2.8 to 4.1 bar)
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

Equipment Cleaning:

Clean spray equipment as soon as possible after use. Flush spray equipment with DeSoto® CN20, DeSoto® CN44, or Desoclean™ 45 high performance solvent cleaner.

Physical Properties (product)



Color: Yellow



Gloss: Not Applicable



Dry Times	13 - 21°C (55 - 70°F)	22 - 28°C (71 - 84°F)	>29°C (>85°F)
Dust Free	45 minutes	30 minutes	20 minutes
Tack Free	75 minutes	60 minutes	45 minutes
Dry to Tape	3 hours	2 hours	1 ½ hours
Dry to Topcoat	2 - 72 hours	2 - 72 hours	2 - 72 hours
Dry to Fly	72 hours	48 hours	24 hours
Full Cure	7 days	7 days	7 days

Accelerated cure:

Allow 30 minutes flash off at 24°C ± 3°C (75°F ± 10°F)
followed by 60 minutes at 49°C (120°F)



Desoprime™ HS CA7233 Military Epoxy Primer



VOC:

Mixed, ready to use VOC (EPA method 24)	340 grams/liter
Base Component	367 grams/liter
Activator Component	258 grams/liter



Flash point:

Base Component	16°C (60°F)
Activator Component	-4°C (24°F)

Shelf Life:


12 months from date of manufacture according to the specification. Consult the specification to verify shelf life requirements.

24 months from date of manufacture for PRC-DeSoto Standard.

Note: Shelf life is provided for original, unopened containers.

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

Note: When procuring to a qualified material specification, follow those storage instructions.



Desoprime™ HS CA7233 Military Epoxy Primer

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at: www.ppgaerospace.com

For sales and ordering information call the local PPG office at the numbers listed below:

Asia Pacific

ASC – Australia

Tel 61 (3) 9335 1557
Fax 61 (3) 9335 3490

ASC – Japan

Tel 81 561 35 5200
Fax 81 561 35 5201

ASC – South East Asia

Tel 65 6861 1119
Fax 65 6861 6162

ASC – Suzhou

Tel (86-512) 6661 5858
Fax (86-512) 6661 6868

ASC – Tianjin

Tel (86-022) 2482 8625
Fax (86-022) 2482 8600

Americas

1 (818) 362-6711 or 1-800-AEROMIX

Europe and Middle East

ASC – Central Europe

Tel 49 (40) 742 193 10
Fax 49 (40) 742 139 69

ASC – Middle East & India

Tel (971) 4 883 9666
Fax (971) 4 883 9665

ASC – North Europe

Tel 44 (0) 1388 770222
Fax 44 (0) 1388 770288

ASC – South Europe

Tel 33 (0) 235 53 43 71
Fax 33 (0) 235 53 54 44

Desoclean, Desoprime, Desothane, DeSoto, and Skydrol are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.
12780 San Fernando Road
Sylmar, CA 91342

www.ppgaerospace.com

Issue Date: 7/17
Lit: 3083