

- Aviation
 - 7.55 cSt synthetic lubricant
 - Good high temperature performance and load carrying

Eastman™ Turbo Oil 274 is now being used by over 50 airlines throughout the world. This represents nearly two-thirds of the world's commercial requirement for 7.5 centistoke turbo oils. This fact is proof of this product's outstanding performance in today's engines and accessories.

Eastman™ Turbo Oil 274 is a DEF STAN 91-98 oil in the 7.5 cSt viscosity class, uniquely suited for older turboprop applications, such as the R-R Dart.

The popularity of Eastman™ Turbo Oil 274 is largely due to its good high temperature performance and load-carrying ability. These provide long trouble-free performance under severe conditions

Synthetic oils of this type are not all identical. The advantages of Eastman™ Turbo Oil 274 are achieved only by careful selection and balance of base stocks and additives to provide the desired performance.

Density @ 15°C	ASTM D 1298	0.9516 kg/L
Viscosity, Kinematic		
@ 100°C	ASTM D 445	7.6 mm ² /s
@ 40°C	ASTM D 445	33.3 mm ² /s
@ -40°C after 35 minutes	ASTM D 2532	11,000 mm ² /s
Pour Point	ASTM D 97	-59°C
Flash Point	ASTM D 92	235°C
Total Acid Number	SAE ARP5088	0.24 mg KOH/g
Nitrile elastomer swell 192 hrs @ 150°C	FED-STD-791, 3604	23.2% vol
Silicone elastomer swell 192 hrs @ 100°C	FED-STD-791, 3604	6.7% vol
Foaming Volume		
Sequence 1 @ 24°C	ASTM D 892	5/0 ml/vol
Sequence 2 @ 93 °C	ASTM D 892	20/0 ml/vol
Sequence 3 @ 24°C	ASTM D 892	10/0 ml/vol

IAE gear test

2000 rpm	IP 166	101.4% of reference
6000 rpm	IP 166	106.3% of reference

Corrosion & Oxidative Stability

Viscosity change @ 37.8°C	ASTM D 4636	13.5
Total Acid Number	ASTM D 4636	-1.38 mg KOH/g
Copper Weight Change	ASTM D 4636	-1.50 mg/cm ²
Magnesium Weight Change	ASTM D 4636	0.00 mg/cm ²
Aluminium Weight Change	ASTM D 4636	0.00 mg/cm ²
Iron Weight Change	ASTM D 4636	0.02 mg/cm ²
Silver Weight Change	ASTM D 4636	0.03 mg/cm ²

72 hrs @ 175°C; ASTM D4636, Alternate Procedure 2

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

06-Oct-2014 9:40:58 AM