

CONFOR™ Foam Family

175

The standard CONFOR product line is being replaced with two updated versions. Both the new CONFOR M foam and the CONFOR AC foam have the same slow recovery attributes as our current standard foams. The CONFOR M and CONFOR AC foams are both RoHS Compliant. Additionally, the CONFOR AC foam meets CAL 117 and FAR 25.253 (a) requirements.

CONFOR CF-40 Foam Series

Typical Property	Test Method	CF-40M	CF-40AC	CF-40
Density Nominal kg/m ³ (lb/ft ³)	ASTM D3574	96 (6.0)	96 (6.0)	96 (6.0)
Flammability	UL 94 (Minimum thickness stated) FMVSS-302 FAR 25.853(a) Appendix F Part I (a)(1)(ii)(12 sec) CAL 117 RoHS Compliant	Listed HBF @ 3mm Meets No No Yes	Meets HF-1 @ 3 mm Meets Meets Meets Yes	Listed HBF @ 6mm Meets Meets Meets No
Ball Rebound %	ASTM D3574	<1	1	<1
Thermal Conductivity – K Value	ASTM C177 W/m*K (BTU in/hr ft ² F)	.040 (0.28)	0.040 (0.28)	0.040 (0.28)
Compression Set (%) 22 hr @ 22C (72F) Compressed 50%	ASTM D3574	1.2	<1	<1
Indentation Force Deflection	ASTM D3574 Test B1 Modified 25% Deflection for 12"x12"x2" sample 22C (72F) @ 50% Relative Humidity N (lbf)	97 (22)	97 (22)	97 (22)
Tensile Strength kPa (psi)	ASTM D3574 5.1 mm/min (20 in/min)	48 (7.0)	51 (7.4)	55 (8)
Tear Strength kN/m (lbf/in)	ASTM D3574 51 cm/min (20 in/min) @ 22C (72F)	0.29 (1.7)	0.29 (1.7)	0.33 (1.9)
Compression Load Deflection	ASTM D 3574C *Modified * 12.7mm thick specimen compressed at a rate of 5.1 mm/min	1.4 (0.20) 1.8 (0.26) 2.0 (0.29) 2.3 (0.33) 2.9 (0.42) 3.5 (0.51) 6.0 (0.87) 16 (2.3)	1.5 (0.21) 2.0 (0.28) 2.3 (0.33) 2.6 (0.38) 3.2 (0.47) 4.4 (0.63) 7.5 (1.1) 20 (2.9)	1.4 (0.20) 1.8 (0.26) 1.9 (0.28) 2.2 (0.32) 2.6 (0.37) 3.2 (0.47) 5.1 (0.74) 12 (1.8)

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Aearo Technologies believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond Aearo Technologies's control and uniquely within user's knowledge and control can affect the use and performance of an Aearo Technologies product in a particular application. Given the variety of factors that can affect the use and performance of an Aearo Technologies product, user is solely responsible for evaluating the Aearo Technologies product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable Aearo Technologies product packaging or product literature, Aearo Technologies warrants that each Aearo Technologies product meets the applicable Aearo Technologies product specification at the time Aearo Technologies ships the product. Aearo Technologies MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the Aearo Technologies product does not conform to this warranty, then the sole and exclusive remedy is, at Aearo Technologies's option, replacement of the Aearo Technologies product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, Aearo Technologies will not be liable for any loss or damage arising from the Aearo Technologies product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

7911 Zionsville Road, Indianapolis, IN 46268
Phone: 317-692-3000 Fax: 317-692-3111 Web: www.earsc.com

CONFOR™ Foam Family

CONFOR CF-42 Foam Series

175

Technical Information:

CONFOR™ Foam Family

CONFOR CF-45 Foam Series

Typical Property	Test Method	CF-45M	CF-45AC	CF-45
Density Nominal kg/m ³ (lb/ft ³)	ASTM D3574	96 (6.0)	96 (6.0)	96 (6.0)
Flammability	UL 94 (Minimum thickness stated) FMVSS-302 FAR 25.853(a) Appendix F Part I (a)(1)(ii)(12 sec) CAL 117 RoHS Compliant	Listed HBF @ 3mm Meets No No Yes	Meets HF-1 @ 3 mm Meets Meets Meets Yes	Listed HBF @ 6mm Meets Meets Meets No
Ball Rebound %	ASTM D3574	<1	1.9	<1
Thermal Conductivity -- K Value	ASTM C177 W/m*K (BTU in/hr ft ² F)	.040 (0.28)	0.040 (0.28)	0.040 (0.28)
Compression Set (%) 22 hr @ 22C (72F) Compressed 50%	ASTM D3574	< 1.0	< 1	< 1.0
Indentation Force Deflection	ASTM D3574 Test B1 Modified 25% Deflection for 12"x12"x2" sample 22C (72F) @ 50% Relative Humidity N (lbf)	213 (48)	213 (48)	214 (48)
Tensile Strength kPa (psi)	ASTM D3574 5.1 mm/min (20 in/min)	117 (17)	145 (21)	131 (19)
Tear Strength kN/m (lbf/in)	ASTM D3574 51 cm/min (20 in/min) @ 22C (72F)	0.64 (3.7)	0.73 (4.2)	0.70 (4)
Compression Load Deflection	ASTM D 3574C *Modified * 12.7mm thick specimen compressed at a rate of 5.1 mm/min	3.1 (0.44) 4.2 (0.61) 4.5 (0.66) 5.0 (0.73) 5.9 (0.86) 7.7 (1.1) 12 (1.8) 32 (4.6)	3.9 (0.57) 5.0 (0.72) 5.3 (0.76) 5.9 (0.85) 7.0 (1.0) 9.1 (1.3) 15 (2.1) 36 (5.3)	3.2 (0.46) 4.4 (0.64) 4.7 (0.68) 5.2 (0.75) 6.0 (0.87) 7.6 (1.1) 12 (1.7) 28 (4.1)

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Aearo Technologies believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond Aearo Technologies's control and uniquely within user's knowledge and control can affect the use and performance of a Aearo Technologies product in a particular application. Given the variety of factors that can affect the use and performance of an Aearo Technologies product, user is solely responsible for evaluating the Aearo Technologies product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable Aearo Technologies product packaging or product literature, Aearo Technologies warrants that each Aearo Technologies product meets the applicable Aearo Technologies product specification at the time Aearo Technologies ships the product. Aearo Technologies MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the Aearo Technologies product does not conform to this warranty, then the sole and exclusive remedy is, at Aearo Technologies's option, replacement of the Aearo Technologies product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, Aearo Technologies will not be liable for any loss or damage arising from the Aearo Technologies product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

7911 Zionsville Road, Indianapolis, IN 46268
Phone: 317-692-3000 Fax: 317-692-3111 Web: www.earsc.com

CONFOR™ Foam Family

CONFOR CF-47 Foam Series

Typical Properties	Test Method	CF-47M	CF-47AC	CF-47
Density Nominal kg/m ³ (lb/ft ³)	ASTM D3574	96 (6.0)	96 (6.0)	96 (6.0)
Flammability	UL 94 (Minimum thickness stated) FMVSS-302 FAR 25.853(a) Appendix F Part I (a)(1)(ii)(12 sec) CAL 117 RoHS Compliant	Listed HBF @ 3mm Meets No No Yes	Meets HF-1 @ 3 mm Meets Meets Meets Yes	Listed HBF @ 6mm Meets Meets Meets No
Ball Rebound %	ASTM D3574	<1	2.2	<1
Thermal Conductivity -- K Value	ASTM C177 W/m*K (BTU in/hr ft ² F)	.040 (0.28)	0.040 (0.28)	0.040 (0.28)
Compression Set (%) 22 hr @ 22C (72F) Compressed 50%	ASTM D3574	< 1.0	< 1	< 1.0
Indentation Force Deflection	ASTM D3574 Test B1 Modified 25% Deflection for 12"x12"x2" sample 22C (72F) @ 50% Relative Humidity N (lbf)	280 (63)	280 (63)	280 (63)
Tensile Strength kPa (psi) 5.1 mm/min (20 in/min)	ASTM D3574	152 (22)	193 (28)	172 (25)
Tear Strength kN/m (lbf/in) @ 22C (72F)	ASTM D3574 51 cm/min (20 in/min) @ 22C (72F)	0.82 (4.7)	0.98 (5.6)	0.91 (5.2)
Compression Load Deflection Force @ 10% Compression kPa (psi) Force @ 20% Compression kPa (psi) Force @ 30% Compression kPa (psi) Force @ 40% Compression kPa (psi) Force @ 50% Compression kPa (psi) Force @ 60% Compression kPa (psi) Force @ 70% Compression kPa (psi) Force @ 80% Compression kPa (psi)	ASTM D 3574C *Modified * 12.7mm thick specimen compressed at a rate of 5.1 mm/min	3.9 (0.57) 5.6 (0.82) 5.9 (0.86) 6.5 (0.94) 7.6 (1.1) 9.8 (1.4) 16 (2.3) 40 (5.7)	4.8 (0.69) 6.9 (1.0) 7.2 (1.0) 7.9 (1.1) 9.3 (1.3) 12 (1.7) 20 (2.8) 49 (7.1)	5.3 (0.77) 6.9 (1.0) 7.9 (1.1) 7.9 (1.1) 9.3 (1.3) 12 (1.7) 18 (2.6) 46 (6.6)

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Aearo Technologies believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond Aearo Technologies's control and uniquely within user's knowledge and control can affect the use and performance of a Aearo Technologies product in a particular application. Given the variety of factors that can affect the use and performance of an Aearo Technologies product, user is solely responsible for evaluating the Aearo Technologies product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable Aearo Technologies product packaging or product literature, Aearo Technologies warrants that each Aearo Technologies product meets the applicable Aearo Technologies product specification at the time Aearo Technologies ships the product. Aearo Technologies MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the Aearo Technologies product does not conform to this warranty, then the sole and exclusive remedy is, at Aearo Technologies's option, replacement of the Aearo Technologies product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, Aearo Technologies will not be liable for any loss or damage arising from the Aearo Technologies product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

7911 Zionsville Road, Indianapolis, IN 46268
Phone: 317-692-3000 Fax: 317-692-3111 Web: www.earsc.com

CONFOR is a trademark of Aearo Technologies LLC

Aearo Technologies LLC • a 3M company

3M and E-A-R are trademarks of 3M Company
© 3M 2013. All rights reserved
Printed 8.13