

ENGINEERING STEELS - HEAT TREATABLE AND NITRIDING STEELS

Application Segments

Aerospace

Available Product Variants

Long Products

Product Description

BÖHLER V354 is an alloyed Cr-Mo-V quenched and tempered steel for high strength and high temperature requirements, good weldability and suitable for nitriding. Insensitive to tempering embrittlement due to Mo content.

Mainly for components in the aerospace industry to be welded and nitrided with high quenched and tempered strength, at operating temperatures from -75° C to 500° C.

Process Melting

Airmelted

Applications

> Structural parts (Aerospace)

> Other Aerospace Components

> Aerospace

Technical data

Material designation		Standards	
1.7734	Market grade	1.7734	WL
15CDV6			
1.7734	SEL		

Chemical composition (wt. %)

C	Si	Mn	P	S	Cr	Mo	V
0.12 to 0.18	max. 0.20	0.80 to 1.10	max. 0.020	max. 0.015	1.25 to 1.50	0.80 to 1.00	0.20 to 0.30

Related to WL 1.7734

Delivery condition

Annealed

Hardness (HB)	max. 197 Bars from 5 to 250 mm diameter
---------------	---

Hardened and Tempered

Tensile Strength (MPa)	min. 700 from 5 to 250 mm diameter
Yield Strength (MPa)	min. 550 from 5 to 250 mm diameter

Hardened and Tempered

Tensile Strength (MPa)	980 to 1,180 from 5 to 100 mm diameter
Yield Strength (MPa)	min. 790 from 5 to 100 mm diameter

Hardened and Tempered

Tensile Strength (MPa)	1,080 to 1,250 from 5 to 100 mm diameter
Yield Strength (MPa)	min. 930 from 5 to 100 mm diameter

Round Bars and Wire Rod (if any)

Diameter mm			MOQ ex mill kg	Length m			Tolerance
ROLLED							
5.01	-	12.49	850	3.00	-	4.00	IT h/k 11
12.50	-	55.00	1,000	3.00	-	4.00	IT h/k 11
55.01	-	69.00	1,200	3.00	-	4.00	IT h/k 11
69.01	-	72.00	1,000	3.00	-	4.00	IT h/k 11
72.01	-	82.00	1,150	3.00	-	4.00	IT h/k 11
82.01	-	120.00	1,400	3.00	-	4.00	IT h/k 11
120.01	-	150.00	1,400	3.00	-	5.00	IT h/k 14
FORGED							
150.01	-	152.00	1,200	2.00	-	5.00	IT h/k 14
152.01	-	192.00	950	2.00	-	5.00	IT h/k 14
192.01	-	203.20	1,440	2.00	-	5.00	IT h/k 14

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@bohler-edelstahl.at

<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.